

# dupré MICRON GRADE

EXFOLIATED VERMICULITE



## DESCRIPTION

This product is a grade of exfoliated vermiculite having a controlled particle size distribution.

## TYPICAL PROPERTIES

Typical Properties of Micron Grade			Typical Physical Properties		Typical Chemical Properties <sup>1</sup>		
Dry Sieve Analysis (% Retained Non-cumulative)	+1.7 mm	0 – 0.5	Melting Point (°C)	~1330	% SiO <sub>2</sub>	38.1	
	+1.0 mm	0 – 7.5	Specific Heat (1kJ kg <sup>-1</sup> K <sup>-1</sup> )	1.08	% MgO	22.7	
	+0.5 mm	45 – 75	Specific Gravity (Crude)	~2.75	% Al <sub>2</sub> O <sub>3</sub>	8.9	
	+0.18 mm	20 – 55	Moh's Hardness (Crude)	1 – 2	% K <sub>2</sub> O	5.4	
	+0.106 mm	0 – 10	pH (ISO 787-9)	7 – 9	% Fe <sub>2</sub> O <sub>3</sub>	8.2	
	-0.106 mm	0 – 5	% Loss at 105°C (Product)	< 1.5	% CaO	3.1	
Loose Bulk Density (g l <sup>-1</sup> )			90 – 150	% Loss at 1000°C (Product)	< 10	% TiO <sub>2</sub>	1.0
						% F	0.6



## APPLICATIONS

- Friction.
- Animal Feed.

## PACKAGING AND STORAGE

Exfoliated vermiculite is supplied in bulk bags or ~100 litre pre-packed plastic bags

Keep in original packaging, in dry conditions and store in a way to prevent any accidental damage and creation of dust.

<sup>1</sup> based on primary vermiculite source

dupré  
**Minerals**

[www.dupreminerals.com](http://www.dupreminerals.com)

Dupré Minerals Limited, Spencroft Road, Newcastle-under-Lyme, Staffordshire, ST5 9JE

Telephone +44 1782 383000 Fax +44 1782 383101 Email [info@dupreminerals.com](mailto:info@dupreminerals.com)

*Information presented above is given in good faith as accurate and reliable but is not to be taken as a guarantee. The figures provided are intended to be a guide to expected average values and should not be interpreted as a specification. Any potential applications referred to are not to be construed as recommendations. It is the responsibility of the user to determine suitability for any specific purpose.*

ISSUE 290818