

# SILVAPERL PERLITE P35

STANDARD

NON-COMBUSTIBLE ULTRA-LIGHTWEIGHT MINERAL AGGREGATE  
WITH EXCELLENT INSULATION & ADSORPTION PROPERTIES

## CHEMICAL PROPERTIES

Perlite is an aluminosilicate glass.

### TYPICAL CHEMICAL COMPOSITION:

Silicon as SiO <sub>2</sub>	73%
Aluminium as Al <sub>2</sub> O <sub>3</sub>	15%
Iron as Fe <sub>2</sub> O <sub>3</sub>	2%
Sodium as Na <sub>2</sub> O	3%
Potassium as K <sub>2</sub> O	5%
Calcium as CaO + Magnesium as MgO	1%
Others	1%
Organic Matter	nil
Moisture Content (when packed)	less than 0.8%

### PHYSICAL PROPERTIES:

Refractive Index	1.5
Free Moisture (max)	< 0.50%
pH of Water Slurry	6.5 - 7.5
Softening Point	890 – 1100 °C
Fusion Point	1280 – 1350 °C
Specific Heat	837 J kg <sup>-1</sup> K <sup>-1</sup>
Thermal Conductivity (loose poured)	0.05 W m <sup>-1</sup> K <sup>-1</sup>
Bulk Density	90 - 120 kg m <sup>-3</sup>

## TYPICAL GRADING

SIEVE SIZE (MM)	WEIGHT PASSING (%)
4.750	85 - 100
2.360	30 - 70
1.700	10 - 55
1.180	0 - 25
0.600	0 - 10

## APPLICATIONS

- Paint, grout and general fillers
- Textured coatings
- Lightweight plasters and renders
- Animal and poultry feeds
- Anti-caking additive
- Drying agent
- Refractory applications
- Fireproofing compounds
- Artificial stone
- Chimney lining



[www.SILVAPERL.COM](http://www.SILVAPERL.COM)